

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

24352 D/14 C04 KAOS 10.07.79 KAO SOAP KK 10.07.79-JP-087071 (12.02.81) C05d-01 C05g-03 Caking-resistant potassium-contg. fertiliser compsn. - contains amine salt of opt. solid fatty acid	C(5-A1A, 10-C4E, 12-M11, 12-N9). 4 42
<p>Potassic fertilizer composition has added to it 0.001-0.1 wt. % of one or more cpds. selected from sodium salt, potassium salt, ammonium salt, calcium salt, magnesium salt, iron salt, monoethanolamine salt, diethanolamine salt, triethanolamine salt, monomethylamine salt, dimethylamine salt and trimethylamine salt of 12-18C saturated or unsaturated fatty acid.</p> <p><u>ADVANTAGES</u></p> <p>Caking of the potassic fertilizer during storage can be prevented by addition of the fatty acid salt. Further, fatty acid salt does not produce an unpleasant smell or phytotoxicity. (Although alkylsulphate and alkylbenzenesulphonate show excellent effect in the prevention of caking of nitrogenous fertilizer, they cannot prevent the caking of potassic fertilizers).</p> <p><u>DETAILS</u></p> <p>The addition amount of the fatty acid salt is 0.001-0.1 wt. % preferably 0.005-0.5 wt. %. Potassic fertilizer can be</p>	<p>either naturally occurring one or synthetic one, and contains as major component potassium chloride or potassium sulphate.</p> <p><u>EXAMPLE</u></p> <p>Caking prevention test is conducted using a potassic fertilizer made in Canada. Sodium stearate, potassium laurate and calcium stearate show 99.2%, 97.4% and 98.0% prevention, respectively, at an addition amount of 0.01 wt. %. On the other hand, aluminium stearate and sodium caprate show only 58.2% and 68.8% prevention at an addition amount of 0.01 wt. % (4ppW108).</p> <p>J560:4494</p>